

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problems Mailbox.**

**This Page Blank (uspto)**

PCT/EP 00/08843

EPO - DG 1

22. 01. 2001

PA 333494

REC'D 05 FEB 2001

WIPO PCT

# THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

November 29, 2000

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM  
THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK  
OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT  
APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A  
FILING DATE UNDER 35 USC 111.

APPLICATION NUMBER: 60/163,841

FILING DATE: November 05, 1999

PRIORITY DOCUMENT  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH  
RULE 17.1(a) OR (b)



By Authority of the  
COMMISSIONER OF PATENTS AND TRADEMARKS

*H. L. Jackson*  
H. L. JACKSON  
Certifying Officer

Express Mail Label No.:  
E098648707US


Please type a plus sign (+) inside this box → ☐

PTO/SB/16 (2-98)  
Approved for use through 01/31/2001. OMB 0651-0037  
Patent and Trademark Office, U.S. DEPARTMENT OF COMMERCE  
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

**PROVISIONAL APPLICATION FOR PATENT COVER SHEET**  
This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53 (c).

INVENTOR(S)					
Given Name (first and middle [if any])		Family Name or Surname		Residence (City and either State or Foreign Country)	
Jerney		Jelenic		Schalkhaar, Netherlands	
<input type="checkbox"/> Additional inventors are being named on the _____ separately numbered sheets attached hereto					
TITLE OF THE INVENTION (280 characters max)					
PEROXIDE-TREATED PRODUCTS WITH NO BLOOMING					
Direct all correspondence to: CORRESPONDENCE ADDRESS					
<input type="checkbox"/> Customer Number		<input type="text"/>		<input type="checkbox"/> Place Customer Number Bar Code Label here	
OR Type Customer Number here					
<input checked="" type="checkbox"/> Firm or Individual Name		Akzo Nobel Inc.			
Address		Intellectual Property Department			
Address		7 Livingstone Avenue			
City		Dobbs Ferry		State	NY
Country		U.S.A.		ZIP	10522-3408
		Telephone		914/674-5465	Fax 914/693-4236
ENCLOSED APPLICATION PARTS (check all that apply)					
<input checked="" type="checkbox"/> Specification Number of Pages		19		<input type="checkbox"/> Small Entity Statement	
<input type="checkbox"/> Drawing(s) Number of Sheets		<input type="text"/>		<input type="checkbox"/> Other (specify) <input type="text"/>	
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT (check one)					
<input type="checkbox"/> A check or money order is enclosed to cover the filing fees				FILING FEE AMOUNT (\$)	
<input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number: 01-1350				\$150.00	
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.					
<input checked="" type="checkbox"/> No					
<input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are _____					

Respectfully submitted,

SIGNATURE   
TYPED or PRINTED NAME **Ralph J. Mancini**  
TELEPHONE **(914) 674-5465**

Date **11/15/99**

REGISTRATION NO. **34,054**  
(if appropriate)  
Docket Number: **ACD2731 PRUS**

**USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT**

This collection of information is required by 37 CFR 1.51. The information is used by the public to file (and by the PTO to process) a provisional application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the complete provisional application to the PTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, Washington, D.C., 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Box Provisional Application, Assistant Commissioner for Patents, Washington, D.C., 20231.

Practitioner's Docket No. ACD2731 PRUS**PATENT****IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

In re application of: Jerney Jelenic  
Application No.: 0 / Group No.:  
Filed: Examiner:  
For: Peroxide-Treated Products with No Blooming

Assistant Commissioner for Patents  
Washington, D.C. 20231

**EXPRESS MAIL CERTIFICATE**"Express Mail" label number EM098648707USDate of Deposit November 5, 1999

I hereby state that the following attached paper or fee

1. Provisional Application for Patent Cover Sheet (in duplicate)
2. Provisional Patent Application (15 pgs. of specification,  
3 pgs. of claims & 1 pg. of abstract)
3. Return Receipt Postcard

Is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 C.F.R. § 1.10, on the date indicated above and is addressed to the Assistant Commissioner for Patents, Washington, D.C. 20231.

Diane L. Moxley

Typed or printed name of person mailing paper or fee



Signature of person mailing paper or fee

NOTE: The label number need not be placed on each page. It should, however, be placed on the first page of each separate document, such as, a new application, amendment, assignment, and transmittal letter for a fee, along with the certificate of mailing by "Express Mail." Although the label number may be on checks, such a practice is not required. In order not to deface formal drawings it is suggested that the label number be placed on the back of each formal drawing or the drawings be accompanied by a set of informal drawings on which the label number is placed.

(Express Mail Certificate [8-3])

60163841.110599

## PEROXIDE-TREATED PRODUCTS WITH NO BLOOMING

- 5 The present invention relates to compositions comprising peroxide and a specific copolymer, a process involving the use of peroxides and said copolymer to treat elastomer/polyolefin compositions, and the products obtained by this process. The resulting treated products show essentially no blooming and reduced emission of volatile compounds. Preferably, said
- 10 treatment involves the degradation and/or cross-linking of predominantly a polyolefin or elastomer through reactions initiated by radicals obtained by decomposition of the peroxide. The resulting treated products can be in the form of finished articles or intermediates.
- 15 Typically, products that are obtained through, *inter alia*, a peroxide-initiated treatment, such as a cross-linking process or a degradation process, suffers from blooming of the decomposition products of said peroxide. Furthermore, said decomposition products can be quite volatile in nature and hence be emitted from the treated article/intermediate. Since such blooming/emission is
- 20 undesired, several solutions have been put forward to reduce these phenomena. US patent No. 3,420,891, for instance, proposes to prevent blooming by using certain tris-peroxides. Belgium patent No. 883.693, on the other hand, proposes to use phthalic anhydride in an elastomer composition. According to a non-binding theory as described in this patent, the phthalic
- 25 anhydride reacts with an OH group-bearing decomposition product of the peroxide. While the OH group-bearing decomposition product would lead to blooming, the reaction product with the phthalic anhydride does not. The phthalic anhydride was used in a quantity of at least 2 moles per mole of (difunctional) peroxide used.
- 30 The use of phthalic anhydride, however, has its drawbacks. More particularly,

60163841.110599

the quantity of OH group-bearing peroxide decomposition products formed will depend on the reaction conditions when the peroxide decomposes. If reaction conditions are such that the radicals undergo  $\beta$ -scission, for example, a significantly reduced quantity of OH group-bearing products is formed (i.e. because ketones are formed). Similarly, if ethylenically unsaturated species are present when the peroxide decomposes, the radicals may react with the unsaturated moiety, resulting in fewer OH group-bearing decomposition products. Also, "in-cage" termination reactions might occur, wherein two radical fragments of the peroxide, after one or more rearrangements, terminate with one another. Hence, the quantity of phthalic anhydride needed to react with the OH group-bearing peroxide decomposition products that are formed is dependent on many factors that, more often than not, cannot be controlled beforehand. Consequently, there will hardly ever be stoichiometric quantities of phthalic anhydride and OH group-bearing peroxide decomposition products.

Unfortunately, it is not only the peroxide decomposition products that may bloom or be emitted from the treated article/intermediate. Also phthalic anhydride was observed to cause blooming. As a result, products obtained by a process comprising a peroxide-initiated treatment of a polymer/elastomer composition comprising phthalic anhydride typically will either suffer from blooming/emission of OH group-bearing peroxide decomposition products, or from blooming of excessive phthalic anhydride.

Furthermore, the industry is looking for a solution to the blooming problem that has a good price/performance ratio and, preferably, allows the use of conventional peroxides, such as dicumyl peroxide, bis(tert-butylperoxyisopropyl)benzene, 2,5-bis(tert-butylperoxy)-2,5-dimethylhexane, 2,5-bis(tert-butylperoxy)-2,5-dimethyl-3-hexyne and/or tert-butyl cumyl peroxide, since these peroxides have proven themselves over the years. More preferably, the solution to the blooming problem should not interfere with the treatment, be

60163841-110599

it cross-linking or degradation, so that recipes do not have to be changed other than in adding a certain ingredient.

There has been an ongoing search for peroxide-containing compositions that will satisfy those needs. Surprisingly, we have found that the combination of peroxides and specific olefinic copolymers according to the invention is particularly suitable, and that the use of such a combination leads to a cost-efficient treatment process without significant recipe changes being necessary. The resulting products show essentially no blooming, and the emission of volatile products from the product was reduced in comparison with products wherein the peroxide was used without said polymer/elastomer being present.

The invention is characterized in that peroxide is used in combination with one or more copolymers comprising olefin-derived moieties and one or more anhydride and/or acid groups, the copolymer being used in a quantity of from 0.1 to 500 per cent by weight of the weight of the peroxide.

It is noted that Japanese patent application No. 08157646 discloses the use of such copolymers in elastomer compositions that contain brass and/or brass-plated iron in order to improve the adhesion of the elastomer, after peroxide-initiated vulcanization, to said brass. Such compositions are not the subject of the present invention. Furthermore, this Japanese patent application is silent with respect to blooming/emission of volatile products.

The copolymers containing olefin-derived moieties and anhydride and/or acid groups can be suitably obtained through (random) copolymerization or grafting processes. EP-A-0 429 123, for instance, discloses a suitable process wherein olefins (1), or mixtures of olefins, are reacted with  $\alpha,\beta$ -unsaturated dicarboxylic compounds (2), in the presence of a polymerization inhibitor, and preferably in

60163841-110599



- the substantial absence of the well-known polymerization initiators, at temperatures from about 180°C to about 350°C and at subatmospheric, atmospheric or superatmospheric pressures, but preferably at atmospheric pressure. The reaction is preferably carried out in the absence of oxygen, i.e.
- 5 under an inert (nitrogen) atmosphere. Reaction times can range from about 0.5 to about 15 hours. The inhibitor utilized is said to be used preferably in a quantity of from about 0.01% to about 3% by weight, based on the combined weight of components (1) and (2). Components (1) and (2) may be reacted in a single dose or may be dosed continuously or periodically throughout the
- 10 reaction cycle. The copolymers so obtained may additionally be hydrogenated, for example by heating at 130 – 200°C in the presence of a catalyst, e.g., nickel or palladium. Such hydrogenated compositions typically have improved thermo-oxidative stability.
- 15 Typical examples of preferred copolymers as used according to the present invention are Dapral® PX 200 and Ricobond® as supplied by Akzo Nobel and Ricon Resins Inc., respectively.
- Olefins suitable for use in the copolymer of the invention include propylene,
- 20 butadiene, isobutylene, and C<sub>6</sub> to C<sub>24</sub> α-olefins. Preferred olefins for use in these copolymers have 12 to 18 carbon atoms. More preferably, at least one C<sub>12</sub> to C<sub>18</sub> α-olefin, such as dodecene-1, tridecene-1, tetradecene-1, pentadecene-1, hexadecene-1, heptadecene-1, and octadecene-1, is used.
- 25 Preferred unsaturated anhydride and/or acid moiety-containing compounds used to introduce anhydride and/or acid groups into the copolymer include maleic anhydride; (di)alkyl/aryl-maleic anhydride, such as n-dodecyl maleic anhydride, citraconic anhydride, and maleic phenyl anhydride; (substituted) norbornene-2,3-dicarboxylic anhydride; (meth)acrylic acid; maleic acid; fumaric

60163841.110599

acid; itaconic acid; citraconic acid; and other anhydrides and/or acids with an unsaturated group that can be linked with an olefin.

5 Preferably, the copolymer contains anhydride and/or acid groups derivable from maleic anhydride or methacrylic acid. The copolymers might also be adducts of alkadiene polymers and cyclic or acyclic anhydrides of mono- or dicarboxylic acids containing 4 to 18 carbon atoms as disclosed in US patent No. 4,423,177.

10 Although it is not critical, the copolymers preferably have a composition as obtainable by reacting one or more olefins and one or more anhydride/acid group-containing monomers, with the anhydride/acid group-containing monomers being present in a quantity of 5-75 per cent by weight (%w/w). More preferably, the anhydride/acid group-containing monomers are present in a quantity of 10-50 %w/w.

15 The copolymers were found not to bloom from products comprising them, possibly due to their molecular weight. To avoid blooming, the molecular weight of the copolymer must be over 500, preferably over 800, and more preferably over 1100 Dalton. However, in order to facilitate processing of compositions comprising the copolymer, and to allow for sufficient mobility of the copolymer in the final matrix, the molecular weight of the copolymer must be below 50,000, preferably below 25,000, and more preferably below 15,000. Typically, an alternating copolymer with 5 to 50 repeating units can suitably be used.

25 The quantity of said copolymer that is to be used in the peroxide-containing elastomer/polyolefin compositions can vary over a wide range and can be optimized on the particular composition and the conditions during peroxide decomposition. However, since the copolymer does not bloom at all, it can be used in a more than stoichiometric quantity, based on the quantity of OH group-

60163841-110599

- bearing decomposition products that can be formed by the peroxide (by radical abstraction). Because it is estimated that as little as 50% of the radicals from the decomposing peroxide might actually lead to the formation of OH group-bearing decomposition products, the minimum quantity of copolymer to be used
- 5 in the peroxide-containing elastomer/polyolefin compositions of the invention is such that the total number of anhydride/acid groups of the copolymer equals 50% of the maximum quantity of OH groups that can be formed from the decomposing peroxide. Typically this means that at least 0.1 %w/w of copolymer is present, based on the weight of the peroxide. The maximum
- 10 quantity of copolymer to be used depends on how much of it is tolerated in the product and on economic considerations. Typically, less than 500%w/w is used, based on the weight of the peroxide, since otherwise the mechanical properties of the product may deteriorate. Preferably, the copolymer is present in a quantity of 1-400 %w/w, more preferably in a quantity of 10-300 %w/w, based
- 15 on the weight of the peroxide. Alternatively, one can specify the quantity of copolymer to be used on the weight percentage that ends up in the treated product. In that case, from 0.05 to 10 %w/w of copolymer, preferably 0.5 to 7.5 %w/w, is present in the product.
- 20 The copolymer may be blended/mixed with the polymer/elastomer at any time using conventional equipment, such as a (twin-screw) extruder. Preferably, it is blended/mixed into the polymer/elastomer together with the peroxide and optional further ingredients, so that just one mixing step is required. However, viscosity differences of the compounds to be blended/mixed may dictate
- 25 otherwise. Large viscosity differences, for example, may require that one of the components be introduced in a stepwise fashion to ensure efficient mixing/blending.

It is noted that the term "polymer/elastomer" as used throughout this document

60163841 "110599

is meant to denominate all thermoplastic and/or rubbery polymers. Preferably, the polymer/elastomer is a (co)polymer of propylene and/or a synthetic or natural rubber, including polypropylene (PP), ethylene/propylene copolymers (such as EPM and EPDM), ethylene octene copolymers (EOP), polybutadiene rubber (BR), styrene butadiene rubber (SBR), nitrile butadiene rubber (NBR), hydrogenated nitrile butadiene rubber (HNBR), polychloroprene rubber (CR), silicone rubber (VMQ, MQ), fluoro elastomers (FKM), natural rubber (NR), and thermoplastic vulcanizates (TPV). Preferred types of polymer/elastomer include EPM; EPDM, such as Vistalon®606 and Vistalon®7500 ex Exxon and Buna®EP 6550 and Buna®EP G8450 ex Bayer; EOP, such as Engage®8150 and Engage®8180 ex DuPont-Dow-Elastomer; VMQ, such as Silopren®HV ex Bayer; FKM, such as Viton® products ex DuPont Dow Elastomers, and particularly PP, such as Hostalen®PPT 1070 ex Hoechst. Most preferred are compositions based on synthetic rubbers, since here the blooming phenomenon is most pronounced, such as EPM, EPDM, and EOP.

It is furthermore to be understood that the term "blooming" is used as it is conventionally in the art. Blooming typically is the result of products migrating to the surface of a polymeric/elastomeric article. Whether a product is subject to blooming or not depends on the solubility of the compound and the rate of diffusion. As is conventional, products are considered not to bloom when no changes on the surface are observed (visual inspection) upon storage for a prolonged time at temperatures above the temperatures that may be encountered during projected use of the products.

The peroxide as used in the compositions according to the invention can be any conventional peroxide. Preferably, the peroxides are chosen from products conventionally used in cross-linking and degradation reactions, such as dialkyl peroxides, perketals, peroxyarbonates, peroxydicarbonates, and the like. More

mentioned below, and copolymer with olefin-derived moieties and anhydride and/or acid groups. Typically, such compositions will contain 1-99.9% by weight, based on the total weight of the composition, of additives and/or carrier material and 99-0.1% by weight, based on the weight of the composition, of the copolymer, up to a total of 100%. More preferably, the compositions will contain 10-99% of additives and/or carrier material and 90-1% of the copolymer. Preferred compositions comprise copolymer with olefin-derived moieties and anhydride and/or acid groups, one or more fillers selected from the group consisting of silica, clay, chalk, kaolin, and carbon black, and optional further conventional additives mentioned above.

The treatment of the present invention most often will involve a radically induced cross-linking and/or degradation process. However, depending on the presence of further additives, such as co-agents, monomers, chain transfer agents, initiators, such as NO compounds, also grafting, functionalization and/or chain transfer reactions can be the (main) reason for said treatment. The compositions according to the invention are preferably used in grafting, degradation and/or cross-linking reactions.

The products obtainable by this process, which show essentially no blooming and reduced emission of volatiles, are typically but not limited to: building profiles; automotive profiles; such as sponge door seals and weatherstrips; mechanical goods, such as hose, conveyor belt cover materials, and seals; and the like. Again, the products may be in the final form and shape, or be present as an intermediate that needs further processing. Such an intermediate may be a granulate of treated polymer/elastomer.

As stated above, compositions according to the invention can contain further compounds, such as the usual additives and fillers. Examples of such additives

60163841.110599

preferably, the peroxide or mixture of peroxides that is used comprises a peroxide selected from the group consisting of bis(tert-butylperoxyisopropyl)benzene, dicumyl peroxide, 2,5-bis(tert-butylperoxy)-2,5-dimethylhexane, 2,5-bis(tert-butylperoxy)-2,5-dimethyl-3-hexyne, 1,3,5-  
5 tris(tert-butylperoxyisopropyl)benzene, tert-butyl cumyl peroxide, di-t-butyl peroxide, 1,1-bis(tert-butylperoxy)-3,3,5-trimethylcyclohexane, 1,1-bis(tert-butylperoxy)cyclohexane, n-butyl-4,4-bis(tert-butylperoxy)valerate, ethyl-3,3-bis(tert-butylperoxy)butyrate, tert-butylperoxy 2-ethylhexyl carbonate, tert-butylperoxy isopropyl carbonate, bis(4-tert-butylcyclohexyl) peroxydicarbonate,  
10 bis(2-ethylhexyl) peroxydicarbonate, and tert-butyl peroxybenzoate.

In a further embodiment, the invention relates to compositions comprising peroxide and a copolymer with olefin-derived moieties and anhydride and/or acid groups, which compositions are pre-eminently suited for use in said  
15 treatment step. These compositions, if so desired, may contain further conventional additives, such as plasticizers (e.g. paraffinic oils and/or esters), antioxidants, scorch retarders, and the like, and conventional carrier materials, such as silica and/or chalk. The conventional additives and carrier materials are presented in more detail below. Typically, such compositions will contain 5-60%  
20 by weight, based on the total weight of the composition, of peroxide, 0.1-500% by weight, based on the weight of the peroxide(s), of the copolymer, optional further additives, and 0-50% by weight of carrier material, up to a total of 100%. Preferred compositions comprise one or more peroxides, copolymer with olefin-derived moieties and anhydride and/or acid groups, one or more fillers selected  
25 from the group consisting of silica, clay, chalk, kaolin, and carbon black, and optional further conventional additives.

In a further embodiment, the invention relates to compositions comprising one or more the conventional additives and/or conventional carrier materials, as

60163841-110599

- are: stabilizers, such as inhibitors of oxidative, thermal, or ultraviolet degradation, also known as antioxidants, antidegradants and/or scorch retarders; lubricants; extender oils; pH controlling substances, such as magnesium oxide and calcium carbonate; release agents; vulcanizing agents, such as sulfur; colourants; plasticizers; diluents; accelerators; and the like. Examples of reinforcing or non-reinforcing fillers are: silica, clay, chalk, carbon black, and fibrous materials, such as glass fibers, and the like.

### Experimental

#### 10 Materials used:

Perkadox® 14 R – Di(tert-butylperoxyisopropyl)benzene (ex Akzo Nobel)


Perkadox® 14 40 B pd ex Akzo Nobel)

Keltan® 520 - EPDM (ex DSM)

Carbon black SRF N-772 (ex Cabot)

#### 15 Sunpar® 150– paraffin oil (ex Sunoco)

Dapral® PX 200 –  $\alpha$ -olefin maleicanhydride copolymer (ex Akzo Nobel) of



formula

wherein n is about 30.

Phthalic anhydride (ex Baker)

Cis-hexahydrophthalic anhydride (ex Acros Organics)

#### 20 Succinic anhydride (ex Fluka Chemie )

Methylnorbornene-2,3 dicarboxylic anhydride (ex Acros Organics)

1,2,4,5 benzene tetracarboxylic acid (ex Acros Organics)

1,3,5-tris-(t-butyl-peroxyisopropyl)benzene (ex Akzo Nobel)

#### 25 Abbreviations used:

MAH = maleic anhydride

60163841-110599

MW = molecular weight (of anhydride)

Px-14R = Perkadox® 14 R, 50% by weight of peroxide.

Px-14 = Perkadox® 14 40 B pd, 40% by weight of peroxide

PX-200 = Dapral® PX 200

5

#### Procedures:

Unless stated otherwise, a standard 100 / 50 / 10 compound (100 parts by weight rubber, 50 parts by weight carbon black, and 10 parts by weight paraffin oil) was used as the polymer/elastomer for testing purposes. Compounding, in  
10 a 5-litre internal mixer ex Werner & Pfleiderer, of 1.6 kg Keltan® 520, 0.8 kg carbon black SRF N-772, and 0.16 kg Sunpar® 150, produced this standard compound.

15

Further ingredients, i.e. peroxide and reactive additive, were used in said standard compound for evaluation. The ingredients were incorporated into the compound on a two-roll mill (Schwabenthal 150x350mm) at a starting temperature of about 50°C. The cross-linking of the resulting 2 mm rubber sheet was done by compression moulding at 175°C for 15 minutes, in which step virtually all peroxide was decomposed.

20

The extractable matter in the rubber, after cross-linking, was determined by extraction with dichloromethane and subsequent GC-analysis. The quantity of extractable matter is an indication of the likelihood that the treated product will show blooming or emit volatile matter.

25

Some products were evaluated using dynamic head space GC analysis to determine the quantity of volatile matter in the product. To this end, a sample of 30-50 mg of the product was heated in a glass tube under a stream of inert gas. The desorbed volatile compounds were trapped in a liquid nitrogen cooled trap

60163841.110599



placed downstream of the sample. After the heat cycle "desorption time" the cold trap was heated rapidly and the condensed volatile compounds evaporated. The compounds were transferred directly to a capillary GC column and separated by means of normal GC analysis. The heating  
5 temperature/desorption time was either 90°C/30 minutes (cycle A) or 120°C/60 minutes (cycle B).

The total GC peaks surface area was tallied up and given as toluene equivalents (ppm toluene), being the quantity of toluene that would give the same peak area when analyzed under the same conditions.

10

The blooming of peroxide decomposition products and other ingredients on the surface of rubber sheets was determined visually. The sheets were stored in sealed glass bottles at room temperature. After a defined time period (1 week /  
15 sheets remained glossy, they were said not to show blooming. When the surface was not glossy or was covered with crystals, the sheets were said to show blooming.

#### Example 1 and Comparative Examples A-F

20 In all examples 6.6 g of Px-14 R (9.75 mmol peroxide) were used per 160 g of standard compound and a further additive/copolymer was used as given in Table 1. The quantity added was again expressed in grams per 160 g of standard compound. "MAH (meq)" stands for the quantity of reactive anhydride/acid groups as introduced by the additive(copolymer).

25

60163841 110599

Table 1

Example	Additive (Copolymer)	MW (Dalton)	Added (g)	MAH (meq)	Blooming of peroxide / additive	
					1 week	1 month
A	None	-	-	-	Yes	Yes
B	succinic anhydride	100	2	20	Yes	Yes
C	phthalic anhydride	148.1	2	13.5	Yes	Yes
D	1,2 4,5 benzene-tetra carbacid	254	2	15.7	Yes	Yes
E	cis-hexahydro phthalic anhydride	154	1.2	7.8	No	Yes
F	Methylnorbornene-2,3 dicarboxylic anhydride	178	1.4	7.8	No	Yes
1	PX-200 1/1	(308) <sub>n</sub>	3	9.75	No	No

- From the product of Example 1, in total about 1,000 ppm of  $\text{CH}_3\text{C}(\text{O})\text{-C}_6\text{H}_4\text{-C}(\text{CH}_3)_2\text{-OH}$  and  $\text{HO-C}(\text{CH}_3)_2\text{-C}_6\text{H}_4\text{-C}(\text{CH}_3)_2\text{-OH}$  could be extracted, whereas
- 5 Comparative Examples A, E, and F showed extractable levels of these compounds of 3,500-5,500 ppm. Comparative Examples B-D showed low levels of extractables, due to the high amount of anhydride/acid used. However, in these tests the excess anhydride/acid bloomed from the product.
- Head space GC analysis using cycles A and B showed the product of Example
- 10 1 to contain about 500 and 1,700 ppm toluene, respectively, while the product of Comparative Example A contained 1,100 and 3,500 ppm toluene, respectively. Each number is the average result of two samples.

#### Examples 2-5 and Comparative Examples G and H

- 15 The previous examples were repeated, except that 4.2 g of Px-14 (4.96 mmol) were used per 160 g of standard compound. The total quantity of extractable

60163844-110599

HO-C(CH<sub>3</sub>)<sub>2</sub>-C<sub>6</sub>H<sub>4</sub>-C(CH<sub>3</sub>)<sub>2</sub>-OH was also determined. The results are given in Table 2.

Table 2

Example	Copolymer	Added	MAH (meq)	Blooming of peroxide / additive		Extraction (ppm)
				1 week	1 month	
G	None	-	-	Yes	Yes	1210
2	PX-200 1/1	1	3.25	No	Yes	375
3	PX-200 1/1	2	6.5	No	Yes	105
H	None	-	-	Yes	Yes	1740
4	PX-200 1/1	3	9.75	No	No	70
5	PX-200 1/1	4	13.0	No	No	40

5

Clearly, the combination of peroxide and copolymer leads to a reduction of volatile/extractable material in the cross-linked product, and non-blooming products can be obtained. The quantity of copolymer needed to obtain non-blooming formulations will be dependent on the actual reaction conditions, but can be evaluated simply by the above-mentioned method.

Head space GC analysis using cycles A and B showed the product of Example 3 to contain 550 and 1,850 ppm toluene, respectively, whereas the product of Comparative Example G contained 700 and 2,000 ppm toluene, respectively. Similarly, the product of Example 4 contained 350 and 1,150 ppm toluene, respectively, while the product of Comparative Example H contained 1,000 and 2,500 ppm toluene, respectively. Again, each number is the average result of two samples.

15

#### Example 6 and Comparative Example I

The previous examples were repeated, except that 2.4 g of 1,3,5-tris-(t-butyl-

20

50163841-110599

peroxyisopropyl)benzene (5 mmol) were used per 160 g of standard compound. In Comparative Example I no copolymer was used, while Example 6 used 2 g of PX-200 1/1. After one month the product of Comparative Example I showed blooming, while the product of Example 6 did not.

- 5 When analyzed for extractable/volatile matter, the product of Example 6 showed that a total of 2,180 ppm of  $C_6H_5-(C(CH_3)_2-OH)_3$  and  $CH_3C(O)-C_6H_5-(C(CH_3)_2-OH)_2$  could be extracted, while the product of Comparative Example I contained 4,500 ppm of such extractable compounds.

- 10 Head space GC analysis using cycles A and B showed the product of Example 6 to contain 150 and 850 ppm toluene, respectively, while the product of Comparative Example I contained 165 and 1,700 ppm toluene, respectively. Each number is the average result of two samples.

60163841-110599

Claims

- 5 1. Process wherein a composition comprising a polymer/elastomer and at least one peroxide is subjected to heat to form free radicals by decomposition of the peroxide and allowing the radicals to react with the polymer/elastomer, resulting in a treated polymer/elastomer product, characterized in that one or more copolymers comprising olefin-derived moieties as well as anhydride and/or acid groups are present in said composition in a quantity of from 0.05 to 10 per cent by weight of the total composition, with the proviso that if said
- 10 copolymer is a maleic anhydride-modified polybutadiene, then the compositions do not contain both an elastomer and brass.
- 15 2. Process according to claim 1 wherein said reaction of the radicals and polymer/elastomer involves the grafting, degradation and/or cross-linking, preferably the degradation and/or cross-linking, of the polymer/elastomer.
- 20 3. Process according to claim 1 or 2 wherein the polymer/elastomer is selected from polyolefins and elastomers, preferably from the group consisting of polypropylene, ethylene propylene copolymer, ethylene octene copolymer, and ethylene propylene diene copolymer.
- 25 4. Process according to any one of the preceding claims wherein the copolymer with olefin-derived moieties and anhydride and/or acid groups has a molecular weight from 500 to 50,000.
5. Process according to claim 4 wherein the copolymer comprises olefinic units derived from ethylene, propylene, butadiene, isobutylene, and/or  $C_6$  to  $C_{24}$  ( $\alpha$ -)olefins, preferably  $C_{12}$  to  $C_{18}$  olefins, and anhydride/acid groups derived from maleic anhydride, (di)alkyl/aryl-maleic anhydride, (substituted)

60163841-110599

norbornene-2,3-dicarboxylic anhydride, (meth)acrylic acid, maleic acid, fumaric acid, itaconic acid and/or citraconic acid, preferably from maleic anhydride or methacrylic acid.

5 6. Products obtainable by the process of any one of the preceding claims.

7. Compositions comprising:

- 5-70% by weight, based on the total weight of the composition, of one or more peroxides,
- 10 - 0.1-500% by weight, based on the weight of the peroxide(s), of a copolymer with olefin-derived moieties and anhydride and/or acid groups,
- optional further additives, and
- 0-50% by weight of a carrier material,
- 15 which are suitable for use in the process of claim 1.

8. Composition according to claim 7 wherein the copolymer has a molecular weight from 500 to 50,000.

20 9. Composition according to claim 7 or 8 wherein the copolymer comprises olefinic units derived from propylene, butadiene, isobutylene and/or C<sub>6</sub> to C<sub>24</sub>  $\alpha$ -olefins, preferably C<sub>12</sub> to C<sub>18</sub> olefins, and anhydride/acid groups derived from maleic anhydride; (di)alkyl/aryl-maleic anhydride; such as n-dodecylmaleic anhydride, citraconic anhydride, and maleic phenyl  
25 anhydride; (substituted) norbornene-2,3-dicarboxylic anhydride; (meth)acrylic acid; maleic acid; fumaric acid; itaconic acid and/or citraconic acid, preferably from maleic anhydride or methacrylic acid.

10. Composition according to any one of claims 7-9 wherein the copolymer

60163841-110599

is obtained from monomer mixtures comprising 5-75% by weight of anhydride/acid group-containing monomers.

- 5 11. Compositions containing 1-99.9% by weight, based on the total weight of the composition, of conventional additives and/or conventional carrier materials and 99-0.1% by weight, based on the weight of the composition, of a copolymer with olefin-derived moieties and anhydride and/or acid groups, up to a total of 100%, which are suitable for use in the process of claim 1.

60163841-110599

## Abstract

The invention relates to the use of copolymers comprising olefin-derived as well as anhydride and/or acid moieties in the treatment of polymers/elastomers using free radicals obtained by decomposing a peroxide. Products resulting from such a treatment show essentially no blooming and reduced levels of volatile compounds, compared to products obtained from the same treatment in the absence of said copolymer.

60163841-110599